




merian[®] BÖHLER FOX CEL 85

Cellulosic stick electrode, for vertical-down welding, pipe welding

Classifications							
EN ISO 2560-A	EN ISO 2560-B	AWS A5.5	AWS A5.5M				
E 46 4 1Ni C 2 5	E 55 10-P1 A U	E8010-P1	E5510-P1				
Characteristics and typical fields of application							
<p>Cellulose electrode for vertical-down welding of high strength large diameter pipelines. Highly economical compared with conventional vertical-up welding.</p> <p>Especially recommended for hot passes, filler and cover layers.</p> <p>BÖHLER FOX CEL 85 is one of the most popular cellulosic electrode which meets all the exacting demands of the field welding of cross country pipelines extremely well. Welding is easy also at difficult weather conditions. It ensures highest joint weld quality down to temperatures of $-40\text{ }^{\circ}\text{C}$.</p> <p>BÖHLER FOX CEL 85 can be used in sour gas applications (HIC-Test acc. NACE TM-02-84). Test values for SSC-test are available too.</p>							
Base materials							
L415NB - L485NB, L415MB - L485MB							
API Spec. 5 L: X 56, X 60, X 65, X 70							
Typical analysis of all-weld metal							
	C	Si	Mn	Ni			
wt.-%	0.14	0.15	0.75	0.7			
Mechanical properties of all-weld metal – typical values (min. values)							
Condition	Yield strength R_e	Tensile strength R_m	Elongation A ($L_0=5d_0$)	Impact work ISO-V KV J			
				+20 °C	$\pm 0\text{ }^{\circ}\text{C}$	-20 °C	-40 °C
u	490 (≥ 460)	580 (550 – 680)	23 (≥ 20)	110	105	100	70 (≥ 47)
u untreated, as welded							
Operating data							
	Polarity: DC (+)	Redrying: not allowed	Electrode identification: FOX CEL 85 8010-P1 E 46 4 1Ni C	\varnothing (mm)	L mm	Amps A	
				3.2	350	80 – 130	
				4.0	350	120 – 180	
				5.0	350	160 – 210	
Approvals							
TÜV (01361.), ABS, CE							